

## Prepainted - PP

### GENERAL DESCRIPTION

COLORBOND® Ultra prepainted steel, specifically designed by BlueScope Steel Limited combines long term durability and exceptional corrosion resistance. To determine if warranties apply, please visit the BlueScope Steel website or contact BlueScope Steel Direct for advice.

### TYPICAL USES

Exterior building profiles in applications requiring excellent corrosion resistance and long term durability. Suited to moderately severe marine and industrial environments. For material selection advice, please contact BlueScope Steel Direct.

### AUSTRALIAN STANDARDS

Substrate- AS 1397


Paint Coating- AS/NZS 2728 Type 4

### PREFERRED SUBSTRATES

ZINCALUME® G550S AM150 steel with Activate™ technology

ZINCALUME® G300S AM150 steel with Activate™ technology {Refer Note 8}

Please refer to current price list or BlueScope Steel Limited State Sales Office for availability of colours and dimensions.



CORSTRIP® protective film may be available on request {Refer Note 3}

- ← Finish Coat (Finish Coat + Primer = nominal 25µm) {Refer Notes 4 & 5}
- ← Universal Corrosion Inhibitive Primer
- ← Conversion Coating
- ← ZINCALUME®- Zinc/Aluminium alloy coated steel with Activate™ technology Substrate
- ← Conversion Coating
- ← Universal Corrosion Inhibitive Primer
- ← Backing Coat (Backing Coat + Primer = nominal 10µm total){Refer Note 6}

### ATTRIBUTES TESTED DURING MANUFACTURE

Property	Test & Evaluation Method(s)	Results
<b>Adhesion</b>		
Reverse Impact	AS/NZS 2728 (App. E)	≥10 joules
T-bend	AS/NZS 2728 (App. F)	Maximum 6T. Refer Note 7.
<b>Hardness</b>		
Pencil	AS1580.405.1	HB or harder
<b>Specular gloss</b>		
60° meter	AS/NZS 1580 602.2; ASTM D523 (test & eval)	Nominal ± 10 units

Australia 1800 800 789

COLORBOND®, COLORBOND® Permagard®, COLORBOND® Coolmax®, AQUAPLATE®, CORSTRIP®, WHITEHAVEN™, BRITWITE™, DRUMSTOCK® and BlueScope are trade marks of BlueScope Steel Limited ABN 16 000 011 058.

Please ensure you have the current data sheet for this product as displayed at [steelproducts.bluescopesteel.com.au](http://steelproducts.bluescopesteel.com.au)



## Prepainted - PP

### PRODUCT ATTRIBUTES

Property	Test & Evaluation Method(s)	Results
<b>Flexibility</b>		
T-bend	ASTM D4145	Maximum 10T (no cracking.) Refer Note 7.
<b>Resistance to abrasion</b>		
Scratch	AS/NZS 2331.4.7 (test & eval)	Typically 2000g
<b>Adhesion</b>		
Natural well washed exposure (10 yrs)	AS/NZS 1580.457.1	No flaking or peeling. Refer Notes 9 & 10.
<b>Resistance to humidity</b>		
Cleveland (500 hours)	ASTM D4585; AS/NZS 1580.481.1.9 (Blisters); AS/NZS 1580.408.4 (Adhesion)	Blister density: ≤3. Blister size: ≤S2. No loss of adhesion or corrosion.
<b>Resistance to corrosion</b>		
Salt spray (1000 hours)	AS/NZS 2728 (App. I); ASTM B117; AS 2331.3.1; AS/NZS 1580.481.1.9 (Blisters); AS/NZS 1580.408.4 (Adhesion)	Blister density: ≤2. Blister size: ≤S3. Undercut from score: ≤2mm. No loss of adhesion or corrosion. Refer Note 2.
Kesternich (SO <sub>2</sub> ) (50 cycles)	DIN 50018	Edge creep: <4mm. Refer Note 2.
<b>Resistance to colour change</b>		
Natural well washed exposure (10 yrs)	AS/NZS 1580.457.1 & ASTM D2244 (Colour)	ΔE cielab 2000: Light colour: ≤4 units. Intermediate colour: ≤6 units. Dark colour: ≤10 units. Refer Notes 9 & 10.
QUV (2000 hours)	ASTM G154 & ASTM D2244 (Colour)	ΔE cielab 2000: Intermediate colour: ≤5 units.
<b>Resistance to chalking</b>		
Natural well washed exposure (10 yrs)	AS/NZS 1580.457.1 & AS/NZS 1580.481.1.11 (Chalk Method B)	Chalk rating: ≤4. Refer Notes 9 & 10.
QUV (2000 hours)	ASTM G154 & AS/NZS 1580.481.1.11 (Chalk Method B)	Chalk rating: ≤4.
<b>Resistance to Solvents</b>		
Exposure	ASTM D1308 (3.1.1); ASTM D2244 (Colour); AS/NZS 1580.481.1.9 (Blisters)	No discolouration or blistering. Refer Notes 9 & 11.
<b>Resistance to acids</b>		
Exposure	ASTM D1308 (3.1.1); ASTM D2244 (Colour); AS/NZS 1580.481.1.9 (Blisters)	No discolouration or blistering. Refer Notes 2 & 11.
<b>Resistance to alkalis</b>		
Exposure	ASTM D1308 (3.1.1); ASTM D2244 (Colour); AS/NZS 1580.481.1.9 (Blisters)	No discolouration or blistering. Refer Notes 2 & 11.
<b>Resistance to fire</b>		
Exposure	AS/NZS 1530.3 (test & eval.)	Ignitability index: 0 rating in scale of 0-20 Spread of flame index: 0 rating in scale of 1-10 Heat evolved index: 0 rating in scale of 0-10 Smoke evolved index: 0-1 rating in scale of 0-10.
<b>Resistance to heat</b>		
Exposure 100°C continuous (500 hrs)	ASTM D2244 (Colour)	Colour change: ΔE cielab 2000: ≤3 units.

Australia 1800 800 789

COLORBOND®, COLORBOND® Permagard®, COLORBOND® Coolmax®, AQUAPLATE®, CORSTRIP®, WHITEHAVEN™, BRITOWHITE™, DRUMSTOCK® and BlueScope are trade marks of BlueScope Steel Limited ABN 16 000 011 058.

Please ensure you have the current data sheet for this product as displayed at [steelproducts.bluescopesteel.com.au](http://steelproducts.bluescopesteel.com.au)



## Prepainted - PP

### IMPORTANT NOTES

- 1 All warranties for a product, if any, are subject to eligibility. Terms and conditions apply. Nothing in this document is intended by BlueScope Steel to extend, modify or otherwise affect any stated product warranty. To find out more, please visit the BlueScope steel website or contact Steel Direct for advice.
- 2 Product may not be suitable if it is intended to use COLORBOND® Ultra steel in an exterior application within 200m of salt marine locations, severe industrial or abnormally corrosive environments; in areas not washed by rain, or in applications where it will be wholly or partly buried in the ground. For selection of the most appropriate COLORBOND® steel product, please refer to Technical Bulletins TB1a, TB1b, CTB16, CTB21 and CTB22. Before purchase, you should check on suitability by visiting the BlueScope Steel website or by contacting BlueScope Steel Direct for advice.
- 3 The CORSTRIP® protective film should be removed from the painted steel strip immediately on installation. Sunlight can increase adhesion of the protective film to the painted surface if left uncovered outside.
- 4 Finish Coat - the coating applied to the exposed surface of the prepainted coil which is expected to meet the Performance Requirements.
- 5 The product is supplied with a nominal 25 unit (60°) gloss Finish Coat
- 6 Backing coat - a thin coating applied to the reverse surface of the prepainted coil. It also gives additional durability to the reverse surface during the service life of the product. Performance Requirements are not generally applicable to Backing coats. Where specific Performance Requirements are deemed necessary for the reverse surface coating, "double sided" product should be specified, in which case a topcoat of full nominal thickness will be applied.
- 7 The minimum internal bend diameters for forming processes to achieve no paint cracking (visible using x10 magnification) and to avoid paint adhesion issues are specified by the T-bend flexibility and T-bend adhesion results respectively- where 1T equals the total coated thickness (tct) in mm of the material. These results are based on testing at 20-25°C.
- 8 For most products, the metallurgical ageing process which is inherent in the paint stoving cycle will result in some loss of ductility compared with unpainted product. However, minimum strength levels designated by relevant standards will still be applicable.
- 9 Improper storage or use of non-approved roll-forming lubricants may cause brand transfer and paint blushing, and may adversely affect colour and long term durability. Product in coil or sheet pack form must be kept dry. If the coil or sheet pack becomes wet, it must be separated and dried (refer AS/NZS 2728 Appendix L, and also Technical Bulletin TB7). Contact Steel Direct to obtain advice on appropriate rollforming lubricants.
- 10 Values quoted are for panels exposed in accordance with AS/NZS 2728. Variations for in-situ performance may occur due to complexity of building design and location.
- 11 COLORBOND® Ultra steel has good resistance to accidental spillage of solvents such as methylated spirits, white spirit, mineral turpentine, toluene, trichloroethylene and dilute mineral acids and alkalis. However, all spillages should be immediately removed by water washing and drying.

Australia 1800 800 789

COLORBOND®, COLORBOND® Permagard®, COLORBOND® Coolmax®, AQUAPLATE®, CORSTRIP®, WHITEHAVEN™, BRITIEWITE™, DRUMSTOCK® and BlueScope are trade marks of BlueScope Steel Limited ABN 16 000 011 058.

Please ensure you have the current data sheet for this product as displayed at [steelproducts.bluescopesteel.com.au](http://steelproducts.bluescopesteel.com.au)

